

W. Nr.	EN-DIN	ASTM - UNS	AISI	®	Kg/dm ³
C° ↗ - 600° → 1200° C					
1.4713	X 10 CrAl 7			SICROMAL 8	8,00
1.4724	X 10 CrSiAl 13			SICROMAL 9	8,00
1.4742	X 10 CrAl 18442	S 44200		SICROMAL 10	8,00
1.4749	X 18 CrN 28446			SICROMAL 11 / 4 C 54	8,00
1.4762	X 10 CrAlSi 24	S 44600		SICROMAL 12	8,00
1.4821	X 20 CrNiSi 25.4		327		8,00
1.4828	X 15 CrNiSi 20.12	S 30215 / 30900	302 B / 309		8,00
1.4833	X 6 CrNi 22.13	S 30908	309 (S)		8,00
1.4841	X 15 CrNiSi 25.20	S 31000 / 31400	310 / 314		8,00
1.4845	X 12 CrNi 25.21	S 31008	310 (S)		8,00
1.4864	X 12 NiCrSi 35.16	N 08330	330	INCOLOY DS	8,00
1.4876	X 10 NiCrAlTi 32.20	N 08800		INCOLOY 800 (H / HT)	8,00
1.4878	X 12 CrNiTi 18.9	S 32109	321 H		8,00
1.4893	X 8 CrNiSiN 21.22	S 30815		253 MA	8,00
1.4919	X 6 CrNi Mo 17.13	S 31609	316 H		8,00
1.4948	X 6 CrNi 18.11	S 30409	304 H		8,00
1.4958	X 5 NiCrAlTi 31.20	N 08810		INCOLOY 800 H	8,00
1.4959	X 8 NiCrAlTi 32.21	N 08811		INCOLOY 800 HT	8,00
Ni & Ni ALLOYS					
2.4066	Ni 99.2	N 02200		NICKEL 200	8,90
2.4068	LC Ni 99N 02201			NICKEL 201	8,90
2.4360	NiCu 30 FeN 04400			MONEL 400	8,88
2.4375	NiCu 30 ATN 05500			MONEL K500	8,72
2.4602	NiCr 21 Mo 14 W	N 06022		HASTELLOY C22	8,69
2.4603	NiCr 30 FeMo	N 06030		HASTELLOY G30	8,22
2.4605	NiCr 23 Mo 16 Al	N 06059		ALLOY 59	8,60
2.4610	NiMo 16 Cr 16 Ti	N 06455		HASTELLOY C4	8,82
2.4617	NiMo 28N 10665			HASTELLOY B2	9,27
2.4618	NiCr 22 Mo 6 Cu			HASTELLOY G	8,36
2.4619	NiCr 22 Mo 7 Cu	N 06985		HASTELLOY G3	8,30
2.4630	NiCr 20 TiN 06075			NIMONIC 75	8,51
2.4631	NiCr 20 TiAlN 07080			NIMONIC 80A	8,37
2.4632	NiCr 20 Co 18 Ti	N 07090		NIMONIC 90	8,18
2.4633	NiCr 25 FeAl			ALLOY 602 CA	8,00
2.4634	NiCo 20 Cr 15 Mo Al Ti	N 13021		NIMONIC 105	8,01
2.4642	NiCr 29 FeN 06690			ALLOY 690	8,20
2.4660	NiCr 20 CuMo	N 08020		CARPENTER 20 Cb 3	8,02
2.4663	NiCr 23 Co 12 Mo	N 06617		INCONEL 617	8,55
2.4665	NiCr 22 Fe 18 Mo	N 06002		HASTELLOY X	8,50
2.4668	NiCr 19 NbMo	N 07718		INCONEL 718	8,35
2.4669	NiCr 15 Fe 7 TiAl	N 07750		INCONEL X-750	8,37
2.4778	CoCr 28			UMCO 50	8,10
2.4816	NiCr 15 FeN 06600			INCONEL 600	8,50
2.4819	NiMo 16 Cr 15 W	N 10276		HASTELLOY C276	9,13
2.4851	NiCr 23 FeN 06601			INCONEL 601	8,25
2.4856	NiCr 22 Mo 9 Nb	N 06625		INCONEL 625	8,63
2.4858	NiCr 21 MoN 08825			INCOLOY 825	8,18
Ti - TITANE - TITANIUM - TITAN					
3.7025		R 50250		GRADE I (1)	4,50
3.7035		R 50400		GRADE II (2)	4,50
3.7055		R 50550		GRADE III (3)	4,50
3.7065		R 50700		GRADE IV (4)	4,50
3.7164		R 56400		GRADE V (5)	4,50
3.7235		R 52400		GRADE VII (7)	4,50
3.7225		R 52250		GRADE XI (11)	4,50



snel staal b.v.

P.O. Box 2120
 1990 AC Velsbroek
 The Netherlands
 Tel. (+31) 23 - 535 24 24
 Fax (+31) 23 - 536 55 31
 Email info@snelstaal.nl
 www.snelstaal.nl

W. Nr.	EN-DIN	ASTM - UNS	AISI	®	Kg/dm ³
Cr					
1.4000	X 6 Cr 13	S 40300 / S 41008	403 / 410 S		8,00
1.4002	X 6 CrAl 13	S 40500	405		8,00
1.4005	X 12 CrS 13	S 41600	415		8,00
1.4006	X 10 Cr 13	S 41000	410		8,00
1.4016	X 6 Cr 17	S 43000	430		8,00
1.4021	X 20 Cr 13	S 42000	420 A		8,00
1.4024	X 15 Cr 13	J 91201	420 S		8,00
1.4028	X 30 Cr 13	S 42000	420		8,00
1.4034	X 46 Cr 13		(420)		8,00
1.4057	X 19 CrNi 17.2	S 43100	431		8,00
1.4104	X 14 CrMoS 17	S 43020	430 F		8,00
1.4112	X 90 CrMoV 18	S 44003	440 B		8,00
1.4122	X 35 CrMo 17				8,00
1.4125	X 105 CrMo 17	S 44004 / S 44025	440 C		8,00
1.4510	X 5 CrTi 17	S 43036 / S 43900	30 Ti		8,00
1.4542 / 1.4548	X 5 CrNiCuNb 16.4	S 17400	630	17.4 PH	8,00
1.4568	X 7 CrNiAl 17.7	S 17700	631	17.7 PH	8,00 ³
Cr + Ni					
1.4301	X 5 CrNi 18.10	S 30400	304		8,00
1.4303	X 5 CrNi 18.12	S 30500	305		8,00
1.4305	X 10 CrNiS 18.9	S 30300	303		8,00
1.4306	X 2 CrNi 19.11	S 304031	304 L		8,00
1.4310	X 12 CrNi 17.7	S 30100	301		8,00
1.4311	X 2 CrNiN 18.10	S 30453	304 LN		8,00
1.4335	X 1 CrNi 25.21		310 L	URANUS 65 / SS25L	8,00
1.4361	X 1 CrNiSi 18.15	S 30600		URANUS S1 / ANTINIT	8,00
1.4541	X 6 CrNiTi 18.10	S 32100	321		8,00
1.4550	X 6 CrNiNb 18.10	S 34700	347 (H)		8,00
Cr + Ni + Mo					
1.4401	X 5 CrNiMo 17.12.2	S 31600	316		8,00
1.4404	X 5 CrNiMo 17.13.2	S 31603	316 L		8,00
1.4406	X 2 CrNiMoN 17.12.2	S 31653	316 LN		8,00
1.4429	X 2 CrNiMoN 17.12.3	(S 31653)	316 LN (Mo +)		8,00
1.4435	X 2 CrNiMo 18.14.3	S 31609	316 L (Mo +)		8,00
1.4436	X 5 CrNiMo 17.13.3		316 (Mo +)		8,00
1.4438	X 2 CrNiMo 18.16.4	S 31703	317 L		8,00
1.4439	X 2 CrNiMoN 17.13.5	S 31726	317 LN		8,00
1.4449	X 5 CrNiMo 17.13	S 31700	(317)		8,00
1.4465	X 1 CrNiMoN 25.25.2	N 08310 / S 31050			8,00
1.4466	X 1 CrNiMoN 25.22.2	S 31050			8,00
1.4505	X 4 NiCrMoCuNb 20.18.2				8,00
1.4506	X 5 NiCrMoCuTi 20.18				8,00
1.4529	X 1 NiCrMoCuN 25.20.6	N 08925		VDM 1925	8,00
1.4539	X 1 NiCrMoCu 25.20.5	N 08904	904 L	URANUS B6 / 2 RK 65	8,00
1.4547	X 1 CrNiMoCuN 20.18.7	S 31254	(F 44)	254 SMO	8,00
1.4563	X 1 NiCrMoCu 31.27.4	N 08028		SANICRO 288,00	8,00
1.4571	X 6 CrNiMoTi 17.12.2	S 31635	316 Ti		8,00
1.4577	X 3 CrNiMoTi 25.25				8,00
1.4580	X 6 CrNiMoNb 17.12.2	S 31640	316 Cb/Nb		8,00
1.4583	X 10 CrNiMoNb 18.12		318		8,00
DUPLEX & SUPER-DUPLEX - α / γ					
1.4362	X 2 CrNiN 23.4	S 32304 / S 39230		URANUS 35N / SAF 23.04	8,00
1.4410	X 2 CrNiMoN 25.7.4	S 32750	(F 53)	SAF 2507	8,00
1.4460	X 3 CrNiMoN 27.5.2329	S 32900	329		8,00
1.4462	X 2 CrNiMoN 22.5.3	S 31803 / S 39209	*329 LN) / (F51)	URANUS 45N / SAF 2205	8,00
1.4501	X 2 CrNiMoCuWN 25.7.4	S 32760	(F55)	ZERON 1008,00	8,00
1.4507	X 2 CrNiMoCuN 25.6.3	S 32550	255	URANUS 52 N (*)	8,00
1.4565	X 2 CrNiMnMoNbN 25.18.5.4	S 24565	XM-19	4565 S / DUPLEX + 6 Mo	8,00